

Siloxane Facade Paint with water- beading Effect based on Acronal 290 D with TEGO® Phobe 1500 N

Pos.	Ingredients	P. b. w.
1	Water	22.85
2	TEGO® Foamex 825 ¹	0.20
3	Surfynol E 104 ²	0.30
4	Walocel XM 6000 PV ³	0.40
5	Acticid MBS ⁴	0.10
6	Kronos 2044 ⁵	20.00
7	Sibelite M 3000 ⁶ or Calcimatt ⁷	32.00
8	Ammonia 25 %	0.15
9	Acronal 290 D ⁸	5.00
10	TEGO® Phobe 1500 N ¹	9.00
11	Acronal 290 D ⁸	10.00
		100.00

⁰¹ Evonik Tego Chemie GmbH, Essen

⁰² Air Products (Biesterfeld), Hamburg

⁰³ Wolff, Walsrode

⁰⁴ Thor Chemie, Speyer

⁰⁵ Kronos, Leverkusen

⁰⁶ Quarzwerke, Frechen

⁰⁷ Omya AG, Köln

⁰⁸ BASF, Ludwigshafen