

Silicone Resin Emulsion Paint based on Acronal 290 D with TEGO® Phobe 1650

Pos.	Ingredients	P. b. w.
1	Water	25.55
2	Walocel XM 6000 PV ¹	0.30
3	TEGO® Foamex 855 ²	0.20
4	Acticid MBS ³	0.15
5	Calgon N new ⁴	0.05
6	TEGO® Dispers 715 ² or TEGO® Dispers 716 ²	0.30
7	AMP 90 ⁶	0.10
8	Kronos 2310 ⁷	12.50
9	Socal P 2 ⁸	10.00
10	Omyacarb 5 ⁹	15.00
11	Omyacarb 2 ⁹	10.00
12	Glimmer Mica TG ¹⁰	3.00
13	Sipernat 820 A ¹¹	2.00
14	TEGO® Phobe 1650 ²	7.20
15	Dowanol DPnB	1.00
16	Acronal 290 D ⁵	12.00
17	Rheolate 278 ¹²	0.2
		100.00

⁰¹ Wolff Cellulosics, Walsrode

⁰² Evonik Tego Chemie GmbH, Essen

⁰³ Thor Chemie, Speyer

⁰⁴ BK Giuliani, Ladenburg

⁰⁵ BASF, Ludwigshafen

⁰⁶ Angus Chemie GmbH, Ibbenbüren

⁰⁷ Kronos Titan, Leverkusen

⁰⁸ Solvay, Rheinberg

⁰⁹ Omya, Köln

¹⁰ Quarzwerke, Frechen

¹¹ Evonik Degussa GmbH, Frankfurt

¹² Elementis, Leverkusen