

# Silicate Emulsion Paint based on Acronal S 559 with TEGO® Phobe 1401

Pos.	Ingredients	P. b. w.
1	Water	23.30
2	Betolin V 30 <sup>1</sup>	0,10
3	Sapetin D 20 <sup>1</sup>	0.30
4	Betolin Quart <sup>1</sup>	0.30
5	TEGO® Foamex 855 <sup>2</sup>	0.20
6	Natrosol 250 HHR <sup>3</sup>	0.30
7	Kronos 2310 <sup>4</sup>	10.00
8	Omyacarb 5 <sup>5</sup>	30.00
9	Plastorit 000 <sup>6</sup>	5.00
10	TEGO® Phobe 1401 <sup>2</sup>	3.00
11	Acronal S 559 <sup>7</sup>	6.00
12	Mineral Spirits	1.50
13	Betolin K 28 <sup>1</sup>	20.00
		100.00

<sup>01</sup> Woellner Silikat, Ludwigshafen

<sup>02</sup> Evonik Tego Chemie GmbH, Essen

<sup>03</sup> Hercules, Düsseldorf

<sup>04</sup> Kronos Titan, Leverkusen

<sup>05</sup> Omya, Köln

<sup>06</sup> Luzenac Naintsch, Graz

<sup>07</sup> BASF, Ludwigshafen