

Guiding Formulation No. 3001 based on SILIKOPON® EW

Corrosion-resistant coating for temperatures up to 650 °C/1,200 °F

for

- exhaust tubes for motorcycles
- industrial equipment
- chimneys

1. Mill base: p.b.w.

Pos. 1	SILIKOPON® EW	26.3
Pos. 2	Heucodur Black 9-100 ¹	8.0
Pos. 3	Printex L ²	1.2
Pos. 4	Plastorit 0000 ³	9.2
Pos. 5	Heucophos ZPO ⁴	5.0
Pos. 6	Talc AT extra ⁵	5.1
Pos. 7	Solvesso 100 ⁶	13.0
Pos. 8	Bentone SD 2 ⁷	0.2
Pos. 9	Methoxy propyl acetate	4.5

2. Let down: p.b.w.

Pos.10	SILIKOPON® EW	15.8
Pos.11	Butyl acetate	4.6
Pos.12	Xylene	7.1

¹ Heubach: heat-stable, inorganic pigment

² Evonik Degussa GmbH: carbon black

³ Luzenac: micro mica

⁴ Heubach: anti-corrosion pigment

⁵ Norwegian Talc: talc

⁶ Exxon

⁷ Rheox: anti-sedimentation additive