

## Guiding Formulation No. 402 based on SILIKOPHEN® P 80/MPA – color black

Corrosion-resistant coating for temperatures up to 650 °C/1,200 °F

- industrial equipment
- chimneys
- exhaust tubes

1. Top-coat:		p.b.w.
Pos. 1	SILIKOPHEN® P 80/MPA	36.0
Pos. 2	Heucodur Schwarz 9-100 <sup>1</sup>	8.0
Pos. 3	Printex L <sup>2</sup>	2.0
Pos. 4	Plastorit 0000 <sup>3</sup>	6.0
Pos. 5	Heucophos ZPO <sup>4</sup>	6.0
Pos. 6	Aerosil R 972 <sup>5</sup>	0.5
Pos. 7	Methoxypropyl acetate	30.5
Pos. 8	Butyl acetate	11.0

<sup>1</sup> Heubach: heat-resistant inorganic pigment

<sup>2</sup> Evonik Degussa GmbH: carbon black

<sup>3</sup> Luzenac: micro mica

<sup>4</sup> Heubach: anti-corrosion pigment

<sup>5</sup> Evonik Degussa GmbH: fumed silica