

Guiding Formulation No. 304 based on SILIKOPHEN® P 80/X – color black

Corrosion-resistant coating for temperatures up to 650 °C/1,200 °F

- industrial equipment
- chimneys
- exhaust tubes

1. Top-coat: black		p.b.w.
Pos. 1	SILIKOPHEN® P 80/X	34.4
Pos. 2	Heucodur Schwarz 9–100 ¹	8.0
Pos. 3	Printex L ²	2.0
Pos. 4	Plastorit 0000 ³	6.0
Pos. 5	Heucophos ZPO ⁴	6.0
Pos. 6	Aerosil R 972 ⁵	2.0
Pos. 7	Xylene	30.6
Pos. 8	Butyl acetate	11.0

¹ Heubach: heat-resistant inorganic pigment

² Evonik Degussa GmbH: carbon black

³ Luzenac: micro mica

⁴ Heubach: anti-corrosion pigment

⁵ Evonik Degussa GmbH: fumed silica