

Solventborne, binder-containing pigment concentrates based on different inorganic pigments with TEGO® Dispers 655 and e.g. TEGO® VariPlus TC

Product	Crenox® R-KB-4 (Crenox) PW 6	Bayferrox® 130 M (Lanxess) PR 101	Bayferrox® 130 M (Lanxess) PR 101
C. I.			
TEGO® VariPlus TC (60 % in MPA)	23.5	17.0	–
Laropal® A 81 (60 % in MPA) (BASF)	–	–	17.0
TEGO® Dispers 655	1.0	5.2	5.2
Methoxypropylacetat	10.3	12.3	12.3
Aerosil® 200 (Evonik)*	0.2	0.5	0.5
Pigment	65.0	65.0	65.0
Total	100.0	100.0	100.0
Additive solids on pigment	1.5 %	8 %	8 %
Resin solids on pigment	22 %	16 %	16 %

* rheology modifier