

# Pigment concentrates based on inorganic pigments

## C.I. –

Waterborne, binder-free

<b>Product</b>	<b>Sicotrans® Orange L 2416 (BASF)</b>
Water	46.6
TEGO® Dispers 752 W	16.3
Pigment	37.0
Biocide	0.1
<b>Total</b>	<b>100.0</b>
<b>Additive solids on pigment</b>	<b>22 %</b>

# Pigment concentrates based on organic pigments

## C.I. –

Waterborne, binder-containing

<b>Produkt</b>	<b>Paliotan® Gelb L 1145 (BASF)</b>
Wasser	7.3
TEGO® VariPlus DS 50 (33 %)	28.6
TEGO® Dispers 750 W	12.5
Defoamer*	1.0
Aerosil® 200 (Evonik)**	0.5
Pigment	50.0
Biocide	0.1
<b>Total</b>	<b>100.0</b>
<b>Additive solids on pigment</b>	<b>10 %</b>
<b>Resin solids on pigment</b>	<b>19 %</b>

\* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.

\*\* rheology modifier