

Pigment concentrates based on organic pigments C.I. PB 15:2

Waterborne, binder-free

Product	Heliogen® Blue L 6875 F (BASF)
Water	37.9
TEGO® Dispers 755 W	24.0
Defoamer*	1.0
Pigment	37.0
Biocide	0.1
Total	100.0
Additive solids on pigment	26 %

* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.

Pigment concentrates based on organic pigments C.I. PB 15:2

Waterborne, binder-containing

Product	Heliogen® Blue L 6875 F (BASF)
Water	43.2
TEGO® VariPlus DS 50 (33 %)	18.2
TEGO® Dispers 755 W	7.5
Defoamer*	1.0
Pigment	30.0
Biocide	0.1
Total	100.0
Additive solids on pigment	10 %
Resin solids on pigment	20 %

* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.

Pigment concentrates based on organic pigments C.I. PB 15:2

Solventborne, binder-containing

Product	Heliogen®	Heliogen®	Heliogen®
	Blue L 6975 F (BASF)	Blue L 6975 F (BASF)	Blue L 6975 F (BASF)
Paraloid DM 55 (60 %ig in MPA) (Rohm & Haas)	23.0	–	–
Alftalat AC 290 (70 %) (Solutia)	–	19.7	–
Laropal® A 81 (60 %ig in MPA) (BASF)	–	–	23.0
TEGO® Dispers 710	12.9	12.9	12.9
Methoxypropylacetat	18.9	16.4	14.1
Solvesso 100	25.2	31.0	30.0
Pigment	20.0	20.0	20.0
Total	100.0	100.0	100.0
Additive solids on pigment	23 %	23 %	23 %
Resin solids on pigment	69 %	69 %	69 %