

# Pigment concentrates based on organic pigments C.I. PB 15:6

Waterborne, binder-free

<b>Product</b>	<b>Heliogen* Blue L 6700 F (BASF)</b>
Water (demin.)	42.0
TEGO® Dispers 755 W	21.9
Defoamer*	1.0
Pigment	35.0
Biocide	0.1
<b>Total</b>	<b>100.0</b>
Additive solids on pigment	25 %

\* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.

# Pigment concentrates based on organic pigments C.I. PB 15:6

Waterborne, binder-containing

Product	Heliogen* Blue L 6700 F (BASF)
Water (demin.)	30.7
TEGO® VariPlus DS 50 (33 %)	33.9
TEGO® Dispers 755 W	4.3
Defoamer*	1.0
Pigment	30.0
Biocide	0.1
<b>Total</b>	<b>100.0</b>
Additive solids on pigment	6 %
Resin solids on pigment	37 %

\* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.

# Pigment concentrates based on organic pigments C.I. PB 15:6

Waterborne, universal

<b>Product</b>	<b>Heliogen® Blue L 6700 F (BASF)</b>
Water (demin.)	40.7
TEGO® Dispers 651	23.2
Defoamer*	1.0
Pigment	35.0
Biocide	0.1
<b>Total</b>	<b>100.0</b>
<b>Additive solids on pigment</b>	<b>20 %</b>

\* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.