

# Pigment concentrates based on inorganic pigments C.I. PBk 11

Waterborne, binder-free

<b>Product</b>	<b>Bayferrox® 318 M (Lanxess)</b>
Water (demin.)	18.6
TEGO® Dispers 750 W	24.8
Defoamer*	1.0
Aerosil® 200 (Evonik)**	0.5
Pigment	55.0
Biocide	0.1
<b>Total</b>	<b>100.0</b>
<b>Additive solids on pigment</b>	<b>18 %</b>

\* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.

\*\* rheology modifier

# Pigment concentrates based on inorganic pigments C.I. PBk 11

Waterborne, universal

<b>Product</b>	<b>Bayferrox® 318 M (Lanxess)</b>
Water (demin.)	26.4
TEGO® Dispers 651	16.5
TEGO® Dispers 652	1.0
Defoamer*	1.0
Pigment	55.0
Biocide	0.1
<b>Total</b>	<b>100.0</b>
<b>Additive solids on pigment</b>	<b>9 %</b>

\* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.