

Pigment concentrates based on inorganic pigments

C.I. PBr 24

Waterborne, binder-containing

Product	Sicotan®	Sicotan®
	Yellow L 1912 (BASF)	Yellow L 1912 (BASF)
Water (demin.)	9.6	8.2
Laropal® LR 9008 (35 %) (BASF)	23.0	–
TEGO® VariPlus DS 50 (33 %)	–	24.4
TEGO® Dispers 750 W	9.6	9.6
Defoamer*	2.0	2.0
Aerosil® R972 (Evonik)**	0.7	0.7
Pigment	55.0	55.0
Biocide	0.1	0.1
Total	100.0	100.0
Additive solids on pigment	7 %	7 %
Resin solids on pigment	15 %	15 %

* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.

** rheology modifier

Pigment concentrates based on inorganic pigments

C.I. PBr 24

Waterborne, universal

Product	Pigment Yellow PK 6033 (Ferro)
Water (demin.)	23.9
TEGO® Dispers 651	14.0
TEGO® Dispers 652	1.0
Defoamer*	1.0
Pigment	60.0
Biocide	0.1
Total	100.0
Additive solids on pigment	7 %

* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.